

276 Abby Road, Manchester, NH 03103 USA Tel: 1+ 603.622.7660

Email: lgcusa@lgcgroup.com | Online: lgcstandards.com

Set-Up Sample

Certificate of Analysis

Revision No.: 000

Revision Date: 09/25/2023



Product ID: MBH-1611X SNSUS6-22

Product Description: Tin Setting-up Sample

Description and Intended Use:

This Set-Up Sample (SUS) was processed under a quality management system that is registered/accredited to **ISO 9001.** This SUS is provided in the form of a solid disk. The intended use of this SUS may include, but is not limited to, routine instrument monitoring and drift correction of Arc-Spark OES and XRF Spectrometers.

Assigned Values listed in wt.%									
Ag	0.12	Bi	0.08	Cu	0.12	Ni	0.03	Se	0.002
As	0.3	Cd	0.013	Fe	0.01	Pb	0.96	Te	0.003
Au	0.003	Co	0.002	ln	0.02	Sb	0.15	TI	0.002

Homogeneity:

Homogeneity samples are selected by a systematic sampling procedure. The number of samples may be determined by the equation below, where N_{prod} is the number of units produced and N_{min} is the number of samples used for homogeneity testing. These samples are arranged in a simple randomized design such that each sample is analyzed multiple times. Homogeneity may also have been determined within sample using an applied version of ASTM E826.

$$N_{MIN} = \max(10, \sqrt[3]{N_{PROD}})$$

Instructions for Use:

The test surface is on the opposite side of the labeled surface, which includes the material identification. The assigned values are applicable for the entire thickness of the unit. Each packaged disk has been prepared by finishing the test surface using a lathe or a saw. The user must determine whether additional surface preparation is needed for their analytical technique. The user is cautioned to use care when either resurfacing the disk or performing additional polishing, as these processes may contaminate the surface. If resurfacing for use in an XRF spectrometer, the remaining depth of the disk must be greater than the infinite thickness of the x-ray emission lines being measured (typically 2-5mm in a metal matrix).

Period of Validity:

The assigned value of this material is valid indefinitely provided the material is handled and stored in accordance with the instructions stated on this certificate. The assigned values are nullified if the material is damaged, contaminated, otherwise modified, or used in a manner for which it was not intended.

Chuck Goudreau, Certifying Officer

September 25, 2023

Date Issued



